

# TECHNICAL SHEET

## BITALBIT ALV plus

### Waterproofing membrane made from glass fleece with aluminum foil and elastomere bitumen

**Product description** BITALBIT ALV plus is elastomere bitumen waterproofing membrane made from glass fleece and aluminum reinforcement. The reinforcement is on both sides coated with elastomere bitumen. The membrane is protected on both sides by polymeric sheeting.

**Characteristics of the product** BITALBIT ALV plus meets the demands of the standards EN 13970 and EN 13969 for type A.

Characteristic	EN Method	Unit	Value
Reinforcement	glass fleece with aluminum		
Surface protection	polymeric sheeting / polymeric sheeting		
Length	1848-1	m	≥ 7,5
Width	1848-1	m	≥ 1
Thickness	1849-1	mm	≥ 3,6
Straightness	1848-1	20mm/10m	pass
Water tightness	1928	kPa	≥ 100
Durability of water tightness against artificial ageing (12 weeks at 70°C)	1296/1928	kPa	≥ 60
Resistance to impact	12691/A	mm	≥ 1000
Resistance to static loading	12730/B	kg	≥ 5
Flexibility at low temperature	1109	°C	≤ -15
Resistance to tearing <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12310-1	N	≥ 50 ≥ 50
Shear resistance of joints <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12317-1	N/50 mm	≥ 400 ≥ 300
Water vapor transmission properties	1931	μ	1,6*10 <sup>6</sup> ±10%
Water vapour transmission properties Sd	1931	m	> 1500
Durability of water vapour resistance against artificial ageing	1296/1931	change	< 50%
Reaction to fire	13501-1	Class	E
Chemical resistance	1847/13969 Annex A	-	pass
Tensile properties <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12311-1	N/50mm	≥ 400 ≥ 300
Elongation <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12311-1	%/50mm	≥ 2,0 ≥ 2,0
Content of dangerous substances	Annex ZA	/	no

**Use and installation**

**BITALBIT ALV plus** is used as vapor barrier in flat roof systems. It can also be used in waterproofing systems of the underground parts of objects, especially as protection against radon. The membrane is applied by exceptionally by torching with a 10 cm overlap. Use of this product is especially recommended for the colder seasons period.

**Storage and transport**

The rolls must be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C. The carrier is responsible for the correct transport.

**Disposal  
considerations of  
waste**

For the removal of waste of product, it is necessary to follow the valid local environmental regulations.  
Waste classification: 17 03 02 bituminous mixtures other than those mentioned in 17 03 01.



The product is in conformity with **EN 13969:2004 and EN 13969:2004/A1:2006 Type A and EN 13970:2004 and EN 13970:2004/A1:2006.**

The system of quality and handling of the environment is conforming with EN ISO 9001 and EN ISO 14001.