

# TECHNICAL SHEET

## IZOTEKT P4 plus

### Waterproofing membrane with a polyester reinforcement and with plastomere modified bitumen

**Product description** IZOTEKT P4 plus is a waterproofing membrane made from a polyester reinforcement that is coated on both sides with plastomere modified bitumen. The membrane is protected on both sides by polymeric sheeting.

**Characteristics of the product** IZOTEKT P4 plus meets the demands of the standards EN 13707, 13969 type A and type T. The additions of plastomer give high resistance against higher temperatures, as well as flexibility at low temperatures. The polyester reinforcement gives high elasticity and resistance to static and dynamic strains.

Characteristic	EN Method	Unit	Value
Reinforcement	Polyester fleece		
Surface protection	Polymeric sheeting / Polymeric sheeting		
Length	1848-1	m	≥ 10
Width	1848-1	m	≥ 1
Straightness	1848-1	20 mm/10m	pass
Thickness	1849-1	mm	≥ 3,6
Watertightness	1928	kPa	≥ 100
Durability of water tightness against artificial ageing (12 weeks at 70 ° C)	1296/1928	kPa	≥ 100
Flexibility at low temperature	1109	°C	≤ -10
Flow resistance at elevated temperature	1110	°C	≥ 120
Resistance to tearing <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12310-1	N	≥ 150 ≥ 200
Shear resistance of joints <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12317-1	N/50 mm	≥ 600 ≥ 550
Dimensional stability <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	1107-1	%	≤ 0,3  ≤ 0,3
Water vapor properties "μ"	1931	/	* NPD
Chemical resistance	1847/13707 Annex C	-	pass
Reaction to fire	13501-1	Class	E
External fire performance	13501-5	Class	F <sub>ROOF</sub>
Resistance to static loading	12730/A	kg	≥ 10
Resistance to static loading	12730/B	kg	≥ 20
Resistance to impact	12691/A	mm	≥ 1300
Resistance to impact	12691/B	mm	≥ 1300
Tensile properties <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12311-1	N/50mm	≥ 650 ≥ 550
Elongation <ul style="list-style-type: none"> <li>longitudinal</li> <li>transversal</li> </ul>	12311-1	%/50mm	≥ 35,0 ≥ 35,0
Flexibility at low temperature after artificial ageing by long term exposure to elevated temperature (12 weeks at 70 ° C)	1296/1109	°C	* NPD
Flow resistance at elevated temperature after artificial ageing by long term exposure to elevated temperature (12 weeks at 70 ° C)	1296/1110	°C	* NPD
Content of dangerous substances	Annex ZA	/	no

\* NPD – no performance determined

### Use and installation

**IZOTEKT P4 plus** is used regarding the demands of the standards as an intermediate layer in two or more layered flat roof systems which are protected by a UV-resistant membrane or as protection layer in roofing systems under heavy protection, especially there, where strains because of movements of the construction are expected. It is also used in single-layer waterproofing systems against dampness and in double-layered horizontal and vertical waterproofing systems exposed to pressurized water (hydrostatic pressure). It is installed with welding process with a flame (gas) burner, over the entire surface. The joints are carried out with 10 cm overlaps and must be watertight. The membrane can also be installed by mechanical fastening.

### Storage

The rolls must be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

### Disposal considerations of waste

For the removal of waste of product, it is necessary to follow the valid local environmental regulations. Waste classification: 17 03 02 bituminous mixtures other than those mentioned in 17 03 01.



The product is in conformity with **EN 13707:2004+A2:2009, EN 13969:2004 and EN 13969:2004/A1:2006 Type A and Type T.**

The system of quality and handling of the environment is conforming with EN ISO 9001 and EN ISO 14001.