

TECHNICAL SHEET

IZOELAST P5 DIN

**Waterproofing membrane with a polyester reinforcement
and with elastomere modified bitumen**

Product description IZOELAST P5 DIN is a waterproofing membrane made from a polyester reinforcement that is coated on both sides with elastomere modified bitumen. The membrane is protected on both sides by polymeric sheeting.

Characteristics of the product IZOELAST P5 DIN meets the demands of the standards EN 13707 and 13969 Type T. It meets the technical requirements of the German national regulations DIN SPEC 20000 201 and 202. Due to its exceptional temperature resistance in both cold and high temperatures, it is suitable for installation in all seasons. Mechanical characteristics of reinforcement give the product high resistance against penetration and tearing.

Characteristic	EN Method	Unit	Value
Reinforcement	Polyester fleece		
Surface protection	Polymeric sheeting / Polymeric sheeting		
Length	1848-1	m	≥ 7,5
Width	1848-1	m	≥ 1
Straightness	1848-1	20 mm/10m	pass
Thickness	1849-1	mm	≥ 5,0
Watertightness	1928	kPa	≥ 400
Durability of water tightness against artificial ageing (12 weeks at 70 ° C)	1296/1928	kPa	≥ 400
Flexibility at low temperature	1109	°C	≤ -25
Flow resistance at elevated temperature	1110	°C	≥ 100
Resistance to tearing - longitudinal - transversal	12310-1	N	≥ 300 ≥ 300
Shear resistance of joints - longitudinal - transversal	12317-1	N/50 mm	≥ 900 ≥ 800
Dimensional stability - longitudinal - transversal	1107-1	%	≤ 0,3 ≤ 0,3
Chemical resistance	1847/13707 Annex C	-	pass
Reaction to fire	13501-1	Class	E
External fire performance	13501-5	Class	F _{ROOF}
Resistance to static loading	12730/A	kg	≥ 25
Resistance to static loading	12730/B	kg	≥ 25
Resistance to impact	12691/A	mm	≥ 2000
Resistance to impact	12691/B	mm	≥ 2000
Tensile properties - longitudinal - transversal	12311-1	N/50mm	≥ 900 ≥ 800
Elongation - longitudinal - transversal	12311-1	%/50mm	≥ 40,0 ≥ 40,0
Resistance to root penetration	13948	-	* NPD
Flexibility at low temperature after artificial ageing by long term exposure to elevated temperature (12 weeks at 70 ° C)	1296/1109	°C	* NPD
Flow resistance at elevated temperature after artificial ageing by long term exposure to elevated temperature (12 weeks at 70 ° C)	1296/1110	°C	* NPD
Content of dangerous substances	Annex ZA	/	no

* NPD – no performance determined

Use and installation

IZOELAST P5 DIN is used as an intermediate layer in two- or more layered flat roof systems which are protected by a UV-resistant membrane or as protection layer in roofing systems under heavy protection, especially there, where strains because of movements of the construction are expected. It is also used in single-layer waterproofing systems against dampness and in double-layered horizontal waterproofing systems exposed to pressurized water (hydrostatic pressure). It is installed with welding process with a flame (gas) burner, over the entire surface. The joints are carried out with 10 cm overlaps and must be watertight. The membrane can also be installed by mechanical fastening.

Storage

The rolls must be stored in an upright position, protected against dampness and extreme temperatures. In winter it is recommended to store the rolls before installation for 24 hours at a temperature of over + 5°C.

Disposal considerations of waste

For the removal of waste of product, it is necessary to follow the valid local environmental regulations. Waste classification: 17 03 02 bituminous mixtures other than those mentioned in 17 03 01.



The product is in conformity with **EN 13707:2004+A2:2009**, **EN 13969:2004** and **EN 13969:2004/A1:2006 Type A and Type T** and **SIST 1031:2018**.

The system of quality and handling of the environment is conforming with EN ISO 9001 and EN ISO 14001.